




Dimensional Stability



	Wood Species	Tangential Shrinkage	Radial Shrinkage	Volume Shrinkage	Dimensional Stability
A	Lamboo®	0.10%	0.04%	0.13%	99.9%
B	Accoya®	1.5%	0.8%	2.3%	97.7%
C	Teak	4.2%	2.2%	6.5%	93.5%
D	Radiata Pine	6.0%	3.3%	9.5%	90.5%
E	Scots Pine	7.7%	4.0%	12.0%	88.0%
F	S. Yellow Pine	8.0%	6.1%	14.6%	85.4%